

SOLUTIONS

ENVIRONMENTAL PROTECTION, INC

1567 W. South Airport Rd. Traverse City, Michigan 49686

Phone | 800-0K-LINER Fax | 231-943-2270

www.geomembrane.com

TYPICAL APPLICATIONS:

Lagoons

Ponds

Floating Covers and Similar Containments

Potable Water Containments

Hydroponic Farming Applications

45 mil Reinforced Polypropylene Specifications

Reinforced polypropylene provides a versatile flexible geomembrane liner. The unique three ply construction with a combination of custom fabric reinforcement encapsulated by extruded high performance polypropylene provides a strong, highly chemical resistant liner.

The chemically inert polymer is modified to provide many specialized properties that include excellent flexibility, low thermal coefficient of expansion and contraction, outstanding dimensional stability, wide temperature range for excellent seaming and good chemical resistance in exposed liner applications. All factory and field seams are thermally welded.

Gauge, Nominal (mils) ASTM-D751 $45 \pm 10\%$ Plies Reinforcing Breaking Strength ASTM-D7004 200 x 250lbs. Tear Strength 100 lbs. ASTM-D5884 (lbs. Min.) Low Temperature -40°F ASTM-D2136, 1/8" Mandrel - 4 hrs. **Dimensional Stability** ASTM-D1204 1 % (% Change Max.) (180°F/1 hour) Hydrostatic Resistance ASTM-D751, 350 psi Method A (psi Min.) Puncture Resistance ASTM-D4833 85 lbs min (Index Puncture) 120 lbs Typical Water Absorption <1% ASTM-D471 (Max. % Weight Change) U. V. Resistance ASTM-G155 Pass Xenon Arc, 15,120 kJ/m² total Radiant exposure

Shear Strength (lbs/in, min) ASTM D-882

Factory Fabricated Seams:

Peel Strength (lbs/in, min)

Preserving water resources for future generations

DISTRIBUTOR

ASP Enterprises-STL 1099 Cassens Ind. Ct. Fenton, MO 63026 TF: 800-869-9600 www.aspent.com ASP Enterprises-KC 5301 E. 59th St. Kansas City, MO 64130 TF: 800-519-2304 www.aspent.com ASP Enterprises-Omaha 15263 Cooper St. Omaha, NE 68138 TF: 877-678-8027 www.aspent.com

ASTM D-882

20

200