



PRODUCT DATA SHEET

Style 1215 DT Iowa/Nebraska DOT

PROPERTY	TEST METHOD	MARV
Tensile Strength (Grab)	ASTM D-4632	175/130
Elongation	ASTM D-4632	8%
Puncture	ASTM D-4833	65 lbs
Mullen Burst	ASTM D-3786	275 psi
Trapezoidal Tear	ASTM D-4533	65 lbs
UV Resistance	ASTM D-4355	80% AFTER 500 HRS
Apparent Opening Size (AOS)	ASTM D-4751	30 US Std. Sieve
Percent Open Area (POA)	CW-02215 Mod.	
Permittivity	ASTM D-4491	1.0 sec ⁻¹
Water Flow Rate	ASTM D-4491	90 gpm/ft ²
Roll Sizes		36", 42"

The property values listed above are subject to change without notice.

Willacoochee Industrial Fabrics

Quality at Competitive Prices.

*769 West Main Street
PO Box 599
Willacoochee, GA 31650*

*This is to certify that Style 1215 sold by Willacoochee Industrial Fabrics is
MADE IN THE USA.*

*Larry Booth
President, Willacoochee Industrial Fabrics*